



Product Information

SSP1405L

THERMALLY CONDUCTIVE HEAT TRANSFER COMPOUND

PRODUCT DESCRIPTION

SSP1405L is a medium-bodied thermally conductive, heat sink compound which is designed to meet the demanding applications which require excellent heat transfer and high dielectrics. **SSP1405L** features an application range of -70°F to 450°F, no bleed or separation and excellent dispersion and stability. **SSP1405L** does not dry out, harden or melt.

APPLICATIONS	FEATURES	TYPICAL DATA	
Mounting Studs of Transistors and Diodes Thermocouple Wells Shock & Heat Dissipation in Transistors Thermal Joints Mounting Semi-Conductive Devices Heat Transfer Medium & Ballast	Designed to meet MIL-C-47113 High Thermal Conductivity Low Bleed & Evaporation Water Resistant Excellent Dielectric Excellent Stability Chemically Inactive Hydrolytically Stable	Appearance Temperature Penetration Bleed Evaporation Specific Gravity	White – Opaque -70°F to 450°F 250-300 1 % Max 1 % Max 2.3 +/- .02
DIELECTRIC PROPERTIES		THERMAL CONDUCTIVITY	
Volume Resistivity Dissipation Factor @ 100 Hz Dielectric Constant @ 100 Hz Dielectric Strength @ 50 mil gap	2.18x10 ¹⁴ ohm cm 0.0001 2.99 500 Volts/Mil	BTU-in/hrft ² -°F Cal/sec-cm ² -°C Watt/m-K	0.42 0.0010 3.00

The information shown in the tables above is not intended for use in preparing specifications.

PACKAGING	STORAGE	RESTRICTIONS	SAFETY
5.3 oz. Tube 1 Lb. Jar 10 Lb. Pail 50 Lb. Pail 500 Lb. Drum	When stored in unopened original containers, shelf life is 18-24 months from the date of manufacture. Recommend storage areas do not exceed 100°F.	Not recommended for surfaces that are to be painted. Avoid use in or near highly oxidative chemicals.	Clean silicone compounds with non-polar solvents. Consult with authorized persons on the appropriate use of solvents in your application. MSDS sheets are available upon request. Most are available on the website.

**SSP Compounds and Greases are tested to customer and military specifications.
SSP, Inc. is Registered as ISO 9001.**

Because we cannot foresee or control varied conditions under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose and nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents. Silchem Marketing Inc is an authorized rep/distributor for SSP, Inc. 2004